



Allure, Primary, Scrabble



Primary
PR2 BRAMBLE



Allure
AL3 GOLD RUSH




Primary
PR6 LA MESA



Allure
AL8 TOASTED ALMOND




Allure
AL5 PESTO



Scrabble
S94 GERANIUM



Primary
PR4 CLARET



Allure
AL6 REGENCY RED



Primary
PR1 MOJAVE



Scrabble
S95 SAGEBRUSH



Primary
PR7 FOOTHILLS



Primary
PR3 REGENCY



Allure
AL1 AMETHYST



Allure
AL4 INDIGO



Scrabble
S92 COBALT



Primary
PR5 BENGAL GREY

Pattern	Content	Weight/Width	Repeat	Abrasion ASTM-D-4157 (Double Rubs)	Colorfastness AATCC Test Method 8	Lightfastness AATCC 16E	Seam Slippage ASTM-D-4034	Flame Resistance
Allure Price Level 2	100% Polyester	10 oz./yd. 54" wide	H - 7" V - 8 5/8"	50,000 Double Rubs	Wet - Class 4 Dry - Class 4.5	Class 5 40 Hours	Warp - 94 lbs. Fill - 68 lbs.	Cal. 117 Section E CS-191-53, Class 1 B.S. 5852, Part 1: 1979 Ignition Source 0; Smoldering Cigarette UFAC, Class 1 BIFMA X5.7-1991
Primary Price Level 1	100% Polyolefin	13 oz./yd. 54" wide	H - 1/4" V - 1/2"	70,000 Double Rubs	Wet - Class 5 Dry - Class 4.5	Class 5 60 Hours	Warp - 62 lbs. Fill - 54 lbs.	Cal. 117 Section E CS-191-53, Class 1 B.S. 5852, Part 1: 1979 Ignition Source 0; Smoldering Cigarette UFAC, Class 1 BIFMA X5.7-1991
Scrabble Price Level 2	52% Rayon 48% Polyester	12 oz./yd. 54" wide	H - 4" V - 4"	50,000 Double Rubs	Wet - Class 5 Dry - Class 5	Class 4.5 40 Hours	Warp - 50 lbs. Fill - 45 lbs.	Cal. 117 Section E

NANOTEX Fabric

Cleaning Instructions: Allure, Primary

For water based stains, use mild detergent foam or upholstery shampoo. For oil based stains, spot clean with a dry cleaning solvent, being sure to test area first. Cleaning by a professional service is recommended.

Cleaning Instructions: Scrabble

Clean liquid spills quickly with a dry, clean cloth. For liquid spills, gently blot (do not rub) spill immediately with an absorbent cloth while the spill is still fresh. Wipe off with clean water and a dry, clean cloth if needed.

For Semi-solids:

Try to lift the spot off of the fabric. Working in a circular motion or removing the spill from the side is often the best means to lift spills from the fabric. Change towel surface frequently until spot has been transferred off of the fabric and onto the absorbent cleaning cloth. (Try to avoid pressing the spill or spreading the stain.) Wipe off with clean water and a dry, clean cloth.

For Stubborn spills:

If a spill does not come off with water and a dry, clean cloth, add a mild detergent mixed with water, and repeat circular motion. Wipe off with water and a dry, clean cloth. Do not rub harshly. Remove all soap residue from the surface with clean water. If thorough rinsing does not occur, re-soiling of the affected area can occur.

Note

If the wrong type of cleaner is used, the fabric could be permanently damaged. Some stains may require a second cleaning to achieve satisfactory results. If there is detergent residue causing re-soiling, remove it using a hot water extraction method, using clear water.



MARYLAND CORRECTIONAL ENTERPRISES

7275 Waterloo Road Jessup, Maryland 20794 410-540-5400 Fax: 410-540-5569 www.mce.md.gov